

New Project 19

Make-up Name	Glass 1 & Coating	Glass 2 & Coating	Glass 3 & Coating	Glass 4 & Coating	Inter layer 1	Gap 1	Gap 2	Glazing Slope	Visible Light			Ultra violet	Solar Energy							Thermal Properties	
									Transmittance	Reflectance			Trans UV (τ _{UV} %)	Transmittance	Reflectance		Absorptance	Solar Factor (g%)	Shading Coefficient (sc)	Secondary Heat Transfer (q _i)	U-Value
										Visible (τ _V %)	ρ _V % out	ρ _V % in			Solar (τ _e %)	ρ _e % out					ρ _e % in
Default Make-up 01	Sun Guard® SN 70/35 HT (CE) on Guardian ExtraClear (CE)	Guardian ExtraClear (CE)	ClimaGuard® Premium2 (CE) on Guardian ExtraClear (CE)	Guardian ExtraClear (CE)	PVB Clear 0.76mm (CE)	10% Air, 90% Argon	10% Air, 90% Argon	90	62.2	16.9	18.5	0.1	28.1	42.2	31.7	29.8	32.3	0.37	4.2	0.5	0.546

Calculation Standard: EN 410:2011 / EN 673:2011

Default Make-up 01

Outdoors

GLASS 1	Guardian ExtraClear (CE)	#1 -----
	Thickness = 6mm	#2 SunGuard® SN 70/35 HT (CE)
GAP 1	10% Air, 90% Argon, 16mm	
GLASS 2	Guardian ExtraClear (CE)	#3 -----
	Thickness = 4mm	#4 -----
GAP 2	10% Air, 90% Argon, 16mm	
GLASS 3	Guardian ExtraClear (CE)	#5 ClimaGuard® Premium2 (CE)
	Thickness = 4mm	#6 -----
INTERLAYER 1	PVB Clear 0.76mm (CE)	
GLASS 4	Guardian ExtraClear (CE)	#7 -----
	Thickness = 4mm	#8 -----

Total Unit (Nominal) = 50.762 mm

Slope = 90°

Estimated Nominal Glazing Weight: 44.2 kg/m²

Indoors

Important Notes

Calculations and terms in this report are based on EN 410:2011/EN 673:2011. The performance values shown above represent nominal values for the center of glass with no spacer system or framing. Solar Factor (g) and Secondary Heat Transfer (qi) are not available for sloped glazing, as no calculation method is prescribed by the standard for these attributes.

The KIWA logo and KIWA Validation Report MD - 14/477/GL are provided as evidence of validation of the Guardian Performance Calculator software, program version 4.1, for execution of calculations of luminous and solar characteristics of glazing and thermal transmittance, according to EN 410:2011 and EN 673:2011.

Embodied CO₂ [eq. kg/m²] A1-A3 is estimated based on material Embodied Carbon Factor (ECF), derived from Guardian Glass Regional third-party independently verified and published / current Environmental Product Declarations (EPDs) which are produced to EN 15804 and are compliant with the requirements of ISO 14044, the International Life Cycle Assessment (LCA) standard, and ISO 14025 and ISO 21930, the international standards covering EPD for construction products. The A1-A3 ECF is an estimate of the embodied carbon due to production of that material. The resulting material value should then be multiplied by the square area of glazing to provide an estimate of embodied carbon of the material at the project scale. Embodied CO₂ estimates provided by Guardian represent only values associated with the glass components manufactured by Guardian. The estimated values do not represent in any way a plant-specific and/or product specific guarantee.

Laminated products:

The Performance Calculator allows the user to model a wide variety of laminated glass makeups using different float glass substrates, coatings and interlayer material, including those makeups where the coating faces the interlayer. It is the user's responsibility to assess whether the laminated glass makeup meets relevant regional standards and complies with applicable laminated glass safety regulations.

In addition, when the laminated glass makeup includes a coating facing the interlayer material, there may be a loss of thermal insulation performance and a color change compared to non-embedded coated class.

Non-specular products (translucent or diffuse):

The performance measurement for non-specular (translucent or diffuse) materials such as translucent interlayers or acid etched glass surface, or surface with ceramic frit is limited by the current experimental technologies. Since measurements capture physically only a part of the resulting radiation, calculated performance results provided herein and based on such measurements are not compliant with any standard (including EN 410) and may only be used as a general reference. Actual values may vary significantly based upon exact fabrication process, as well as type, thickness and color of used non-specular material.

Explanation of Terms according to EN 410:2011/EN 673:2011

Visible Light Transmittance (Tv, %) is the percentage of incident light in the wavelength range of 380 nm to 780 nm that is transmitted by the glass.

Ultraviolet (UV) Transmittance (Tuv, %) is the percentage of the incident UV component of the solar radiation in the wavelength range of 280 nm to 380 nm that is transmitted by the glass.

Solar Energy Direct Transmittance (Te, %) is the percentage of incident solar energy in the wavelength range of 300 nm to 2500 nm that is directly transmitted by the glass.

Visible Light Reflectance Outdoors/Indoor (Rv out/in, %) is the percentage of incident visible light directly reflected by the glass.

Solar Direct Reflectance Outdoors/Indoors (Re out/in, %) is the percentage of incident solar energy directly reflected by the glass.

Solar Energy Absorptance (Ae, %) is the percentage of the sun's energy that is absorbed by glass.

U-Value (Ug, W/m² K) is the glazing parameter that characterizes the heat transfer through the central part of the glazing, i.e. without edge effects, and expresses the steady-state density of heat transfer rate per temperature difference between the environmental temperatures on each side. Temperature differential according to standard conditions: ΔT=15K°. The lower the value, the greater is the insulating value. EN 673 defines the value with 1 decimal place. The value is also provided with 3 decimal places for informational purposes.

Solar Factor or Total Solar Energy Transmittance or g-value (g%) is the total solar radiation transmitted by the glass.

Shading Coefficient (sc) is Solar Factor divided by 0.87. It is a measure of the solar heat gain referenced to 3 mm clear glass which has the designated value of 1.00.

Secondary Heat Transfer Coefficient (qi) is the result of heat transfer by convection and longwave IR-radiation of that part of the incident solar radiation which has been absorbed by the glazing.

Colour Rendering Index in transmission, D65 (R_a) is the change in colour of an object as a result of the light being transmitted through the glass.

Disclaimer

This performance analysis is provided for the limited purpose of assisting the user in evaluating the performance of the glass products identified on this report.

Spectral data for products manufactured by Guardian reflect nominal values derived from typical production samples or CE Initial Type Testing and subject to variations due to manufacturing and calculation tolerances. Spectral data for products not manufactured by Guardian were derived from the LBNL International Glazing Database and have not been independently verified by Guardian. Guardian recommends a full-size mock-up be approved.

The values provided herein are generated according to established engineering practices and applicable calculation standards. Many factors may affect glazing characteristics, including glass size, building orientation, shading, wind speed, type of installation, production process and others. The applicability and results of the analysis are directly related to user inputs and any changes in actual conditions can have a significant effect on the results. It is the responsibility of the users of the analysis to ensure that the intended application is appropriate and complies with all relevant laws, regulations, standards, codes of practices, processing guidelines and other requirements. Guardian makes no guarantee that any glazing modeled herein is available from Guardian or any other manufacturer. The user has the responsibility to check with the manufacturer regarding availability of any glass type or make-up.

While Guardian has made a good faith effort to verify the reliability of the tools used for this analysis, they may contain unknown programming errors that could result in inaccurate results. The user assumes all risk relating to the results provided and is solely responsible for selection of appropriate products for user's application. Guardian makes no express or implied warranty of any kind with respect to the tools used by Guardian and this analysis. There are no warranties of merchantability, non-infringement or fitness for a particular purpose with respect to the tools used by Guardian and this analysis and no warranty shall be implied by operation of law or otherwise. The only warranties applicable to Guardian products are those separately provided in writing for each product. In no event shall Guardian be liable for direct, indirect, special, consequential or incidental damages of any kind relating to or resulting from use of Guardian tools and analyses.

Trademarks owned by Guardian Industries, LLC and/or its affiliates may be registered in the United States and other jurisdictions. All other trademarks are property of their respective owners.

User hereby represents and warrants that it is the rightful owner of all intellectual property rights (the "IP Rights") in and to any logos, images, or trademarks user uploads for application in the Guardian Performance Calculator output report. User agrees to indemnify, defend and hold harmless Guardian Industries, LLC and its affiliates, directors, officers, employees, and agents from and against any and all losses, damages, liabilities, claims, demands, suits, judgments, settlements, costs and expenses (including reasonable attorneys' fees and costs) arising out of or in connection with any third-party claim or action that the use of such logos, images or trademarks infringe or misappropriate any other third-party IP Rights. By using a logo, image or trademark, user acknowledges and accepts the terms of this disclaimer and agrees to comply with all applicable laws and regulations governing the use of the logo, image, or trademark.

By accessing this calculator, you agree not to alter or modify the generated report data and information, by any means. Any manual alteration will be your own responsibility and will annul all the content of the report.

Program Version: 4.1.0.9850

Database Version: 20240209